

GloMoldPlus

Product Selection Guide

Product		Standard	Low Temp	High Temp	High Tear	Low Mooney	Non-Curing
Color		Yellow	Red	Orange	Green	Blue	Lavender
Temp/Cure Time	Low	345deg/13min	275deg/20min	385deg/5min	345deg/13min	345deg/13min	160deg
	High	380deg/8min	340deg/14min	450deg/1min	380deg/8min	380deg/8min	400deg
Specific Gravity	g/cm3	1.13	1.13	1.13	1.14	1.28	1.13
Tensile Strength	psi	1220	1220	750	1290	740	N/A
300% Modulus	psi	150	150	670	110	650	N/A
Elongation	%	720	720	270	810	310	N/A
Hardness	Shore A	46	46	55	43	56	N/A
Tear Strength	ppi	111	111	49	178	69	N/A